

| TYPICAL PROPERTIES OF POLYCARBONATES (PC) | | | | |
|---|--|-------------------------|-------------------|----------------------|
| ASTM or UL Test | Property | General Purpose | High Flex Modulus | 20% Glass Reinforced |
| PHYSICAL | | | | |
| D792 | Specific gravity | 1.2 | 1.25 | 1.35 |
| D792 | Specific volume (in³/lb) | 23 | 22.2 | 20.5 |
| D570 | Water absorption, 24 h, 1/8-in thk (%) | 0.15 | 0.12 | 0.16 |
| MECHANICAL | | | | |
| D638 | Tensile strength (psi) | 9,000-10,500 | 8,000-9,600 | 16,000 |
| D638 | Elongation (%) | 110-125 | 10-20 | 4-6 |
| D638 | Tensile modulus (10⁵ psi) | 3.4 | 4.5 | 8.6 |
| D790 | Flexural strength (psi) | 11,000-15,000 | 15,000 | 19,000 |
| D790 | Flexural modulus (10⁵ psi) | 3.0-3.4 | 5.0 | 8.0 |
| D256 | Impact strength, Izod (ft-lb/in of notch) | 12-16 | 2 | 2 |
| D671 | Fatigue endurance limit, 10⁷ cycles (psi) | 1,000 | 2,000 | 5,000 |
| D785 | Hardness, Rockwell M | 62-70 | 85 | 91 |
| THERMAL | | | | |
| C177 | Thermal conductivity (Btu-in/hr-ft²-°F) | 1.35 | 1.41 | 1.47 |
| D696 | Coefficient of thermal expansion (10⁻⁵ in/in-°C) | 6.6-7.0 | 3.2 | 2.7 |
| D648 | Deflection temperature (°F) | At 264 psi At 66 psi | 260-270 280 | 288 295 300 |
| UL 94 | Flammability rating | HB, V-0 | V-2, V-0 | V-2, V-0 |
| ELECTRICAL | | | | |
| D149 | Dielectric strength (V/mil) | Short time, 1/8-in thk | 380-400 | 450 |
| D150 | Dielectric constant | At 1 kHz | 3.02 | — |
| D150 | Dissipation factor | At 1 kHz | 0.0021 | — |
| D257 | Volume resistivity (ohm-cm) | At 73°F, 50% RH | >10 ¹⁶ | >10 ¹⁶ |
| D495 | Arc resistance (s) | 10-120 | 5-120 | 5-120 |
| OPTICAL | | | | |
| D542 | Refractive index | 1.586 | — | — |
| D1003 | Transmittance (%) | 85-89 | — | — |
| FRICTIONAL | | | | |
| Coefficient of friction | | | | |
| Self | | 0.52 | — | — |
| Against steel | | 0.39 | — | — |

| ISO or UL Test | Property | General Purpose | High Flex Modulus | 20% Glass Reinforced |
|-------------------------|--|----------------------------|-------------------|----------------------|
| PHYSICAL | | | | |
| ISO1183 | Specific gravity | 1.2 | 1.25 | 1.35 |
| ISO1183 | Specific volume (cm³/g) | 0.83 | 0.79 | 0.74 |
| ISO62 | Water absorption, 24 h, 3.1 mm thk (%) | 0.15 | 0.12 | 0.16 |
| MECHANICAL | | | | |
| ISO527 | Tensile strength (MPa) | 62.05-72.39 | 55.16-66.19 | 110.32 |
| ISO527 | Elongation (%) | 110-125 | 10-20 | 4-6 |
| ISO527 | Tensile modulus (10³ MPa) | 2.34 | 3.10 | 5.93 |
| ISO178 | Flexural strength (MPa) | 75.84-103.42 | 103.42 | 131.00 |
| ISO178 | Flexural modulus (10³ MPa) | 2.01-2.34 | 3.45 | 5.51 |
| ISO180 | Notched Izod impact strength (J/m) | 641-854 | 107 | 107 |
| ISO2039 | Hardness, Rockwell M | 62-70 | 85 | 91 |
| THERMAL | | | | |
| ISO8302 | Thermal conductivity (W/(mK)) | 0.21 | — | 0.24 |
| ISO11359 | Coefficient of thermal expansion (10⁻⁴ m/m-°C) | 1.28-1.26 | 0.57 | 0.48 |
| ISO75 | Deflection temperature (°C) | At 1.80 MPa At 0.45 MPa | 127-132 138 | 142 146 |
| UL 94 | Flammability rating | HB, V-0 | V-2, V-0 | V-2, V-0 |
| ELECTRICAL | | | | |
| IEC243 | Dielectric strength (kV/mm) | Short time, 3.1 mm thk | 14.9-15.7 | 17.7 |
| IEC250 | Dielectric constant | At 1 kHz | 3.02 | — |
| IEC250 | Dissipation factor | At 1 kHz | 0.0021 | — |
| IEC093 | Volume resistivity (ohm-cm) | At 23°C, 50% RH | >10 ¹⁶ | >10 ¹⁶ |
| ASTM | Arc resistance (s) | 10-120 | 5-120 | 5-120 |
| D495 | OPTICAL | | | |
| ISO489 | Refractive index | 1.586 | — | — |
| ASTM D1003 | Transmittance (%) | 85-89 | — | — |
| FRICTIONAL | | | | |
| Coefficient of friction | | | | |
| Self | | 0.52 | — | — |
| Against steel | | 0.39 | — | — |